



Kinetic Polymers

(AN ISO 9001 - 2008 Certified Company)

D-13/2, Phase-1, Road No. 3, IDA., Jeedimetla, Hyderabad - 055. INDIA
Phones : 7207078344, 7207008277, Telefax : 040-23093957
Email : kineticpolymers@gmail.com / Website : www.kineticpolymers.com



Technical Specification of Antistatic Apron & Caps

Composition	Polyester filament yarn with Conductive filament yarn
Wrap (Polyester filament yarn)	75d / 36f
Wrap (Polyester filament yarn)	100d / 48f
Wrap (Conductive yarn)	97d / 25f
Wrap (Conductive yarn)	97d / 25f
Weaving Structure (twill)	2up / 1 down
Density (wrap x weft / inch)	192 x 92
Weight (gr / yd)	155
Conductive yarn's interval	5 x 5 mm
Material	100 % Poly
Electro Conductive Yarn	Carbon
Air Permeability (cc / cm ² / sec)	9.3
Moisture Permeability (gr / m ² / 24hrs)	7,156
Tearing Strength (gr) Warp	2,992
Weft	2,448
Acid Resistance (50 wash)	Good
Fractional Static Charge (V) Wrap	90
Weft	110
Surface Resistivity (Ohm /Sq)	10 ⁵ – 10 ⁹
Particle Efficiency (%) 0.3	81
0.5	85
Colour	White / Blue
Uses – In Pharma area / clean room	



Note: Normal apron made with cotton rich material are having lints. Which are not advisable in pharma / powder handling area.

Pure polyester cloth is one which can generate heavy static, because of insulating material. Hence not recommended in clean room / pharma area.